Crystal Data: Hexagonal. Point Group: 3m. As crudely formed pseudo-octahedral crystals, to 7 mm; massive.

Physical Properties: Fracture: Uneven. Hardness = 5-5.5 D(meas.) = 4.75(11)D(calc.) = 4.86

Optical Properties: Translucent to opaque. Color: Clove-brown with a reddish tinge; pale layender-brown to colorless in thin fragments. Streak: Grayish white. Luster: Resinous. Optical Class: Uniaxial (+); anomalously biaxial. $\omega = 1.806-1.817$ $\epsilon = 1.808-1.825$ $2V(\text{meas.}) = 0^{\circ}-25^{\circ}$

Cell Data: Space Group: R3c. a = 10.779(6)c = 38.061(7)

X-ray Powder Pattern: Mountain Pass, California, USA. 2.95 (100), 1.954 (50), 3.47 (42), 2.69 (42), 2.83 (38), 3.31 (33), 3.11 (30)

Che	шты	1 V .

	(1)		(1)
SiO_2	22.24	CaO	4.48
${ m TiO}_2$	0.08	BaO	0.45
Al_2O_3	1.14	$\mathrm{Na_2O}$	0.24
La_2O_3	30.04	${ m K_2O}$	0.16
$\mathrm{Ce_2O_3}$	35.05	$\mathrm{H_2O^+}$	2.72
Fe_2O_3	0.92	$\mathrm{H_2O^-}$	0.17
MnO	0.20	SO_3	0.14
MgO	1.90	\mathbf{F}	0.07
		Total	[100.00]

(1) Mountain Pass, California, USA; recalculated to 100% after deduction of 17.7% bastnäsite; corresponds to $(Ce_{3.90}La_{3.37}Ca_{1.63})_{\Sigma=8.90}(Mg_{0.61}Fe_{0.39}^{3+}Na_{0.14}K_{0.06}Ba_{0.05})_{\Sigma=1.25}$ $Si_{6.83}O_{25.68}(OH)_{3.89}$.

Occurrence: In rare-earth-bearing hydrothermal quartz-barite-carbonatite veins in shonkinite (Mountain Pass, California, USA).

Association: Bastnäsite, allanite, epidote, monazite, törnebohmite, fluorite, uraninite, barite, quartz, galena.

Distribution: In Sweden, at the Bastnäs mine, Riddarhyttan, Västmanland. In the USA, from the Mountain Pass district, San Bernardino Co., California, and in Colorado, at Jamestown, Boulder Co. In Canada, from Papineau Co., and Mont Saint-Hilaire, Quebec. In the Kyshtymsk district, Ural Mountains, Russia.

Name: For its *cerium* content; the element was discovered in this mineral and named for the planetoid Ceres, also then just discovered.

Type Material: Harvard University, Cambridge, Massachusetts, USA, 48851.

References: (1) Dana, E.S. (1892) Dana's system of mineralogy, (6th edition), 550. (2) Gay, P. (1957) An X-ray investigation of some rare-earth silicates: cerite, lessingite, beckelite, britholite, and stillwellite. Mineral. Mag., 31, 455–468. (3) Gay, P. (1957) The crystallography of cerite. Amer. Mineral., 42, 429-432. (4) Glass, J.J., H.T. Evans, Jr., M.K. Carron, and F.A. Hillebrand (1958) Cerite from Mountain Pass, San Bernardino County, California. Amer. Mineral., 43, 460-475. (5) Moore, P.B. and J. Shen (1983) Cerite, $RE_{0}(Fe^{3+}, Mg)(SiO_{4})_{6}(SiO_{3}OH)(OH)_{3}$: its crystal structure and relation to whitlockite. Amer. Mineral., 68, 996–1003.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise without the prior written permission of Mineral Data Publishing.