

Fluorcaphite

$\text{Ca}(\text{Sr}, \text{Na}, \text{Ca})(\text{Ca}, \text{Sr}, \text{Ce})_3(\text{PO}_4)_3(\text{F}, \text{OH})$

©2001-2005 Mineral Data Publishing, version 1

Crystal Data: Hexagonal. **Point Group:** 6. Subhedral slender prisms, to 5 mm, in aggregates.

Physical Properties: Tenacity: Brittle. Hardness = 5 D(meas.) = 3.60 D(calc.) = 3.57

Optical Properties: Transparent. Color: Light to bright yellow. Luster: Vitreous.
Optical Class: Uniaxial (-). $\omega = 1.649$ $\epsilon = 1.637$

Cell Data: Space Group: $P6_3$. $a = 9.485(3)$ $c = 7.000(3)$ $Z = 2$

X-ray Powder Pattern: Khibiny massif, Kola Peninsula, Russia.
2.838 (100), 2.740 (53), 2.814 (48), 3.498 (45), 1.865 (31), 3.104 (22), 1.963 (21)

Chemistry:

	(1)		(1)
P_2O_5	36.23	CaO	30.46
SiO_2	0.57	SrO	20.78
La_2O_3	2.61	BaO	0.03
Ce_2O_3	4.78	Na_2O	1.74
Pr_2O_3	0.34	F	2.17
Nd_2O_3	1.48	H_2O	[0.52]
Sm_2O_3	0.14	$-\text{O} = \text{F}_2$	0.91
		Total	[100.94]

(1) Khibiny massif, Kola Peninsula, Russia; by electron microprobe, average of seven analyses; corresponds to $(\text{Ca}_{3.16}\text{Sr}_{1.16}\text{Na}_{0.32})_{\Sigma=4.64}(\text{Ce}_{0.17}\text{La}_{0.10}\text{Nd}_{0.05}\text{Pr}_{0.01})_{\Sigma=0.33}[(\text{PO}_4)_{2.96}(\text{SiO}_4)_{0.06}]_{\Sigma=3.02}[\text{F}_{0.66}(\text{OH})_{0.34}]_{\Sigma=1.00}$, structurally recast as $\text{Ca}_{1.0}(\text{Sr}_{0.5}\text{Na}_{0.3}\text{Ca}_{0.2})_{\Sigma=1.0}(\text{Ca}_{2.1}\text{Sr}_{0.6}\text{Ce}_{0.3})_{\Sigma=3.0}[(\text{PO}_4)_{2.9}(\text{SiO}_4)_{0.1}]_{\Sigma=3.0}[\text{F}_{0.7}(\text{OH})_{0.3}]_{\Sigma=1.0}$.

Occurrence: In miarolitic cavities in a hyperagmatic pegmatite in a differentiated alkalic massif.

Association: Deloneite-(Ce), belovite-(Ce), alkalic amphibole, lamprophyllite, labuntsovite, wadeite, sazykinaite-(Y), remondite-(La), sphalerite, galena, fluorite, graphite.

Distribution: From Mt. Koashva, Khibiny massif, Kola Peninsula, Russia.

Name: For FLUORine, CAlcium, and PHosphorus in the composition.

Type Material: A.E. Fersman Mineralogical Museum, Academy of Sciences, Moscow, Russia.

References: (1) Khomyakov, A.P., I.M. Kulikova, and R.K. Rastsvetaeva (1997) Fluorcaphite $\text{Ca}(\text{Sr}, \text{Na}, \text{Ca})(\text{Ca}, \text{Sr}, \text{Ce})_3(\text{PO}_4)_3\text{F}$ – a new mineral with the apatite structural motif. Zap. Vses. Mineral. Obshch., 126(3), 87–97 (in Russian with English abs.). (2) (1998) Amer. Mineral., 83, 907–908 (abs. ref. 1). (3) Rastsvetaeva, R.K. and A.P. Khomyakov (1996) Structural features of a new naturally occurring representative of the fluorapatite-deloneite series. Kristallografiya (Sov. Phys. Crystal.), 41, 831–834 (in Russian). (4) Pekov, I.V. (1998) Minerals first discovered on the territory of the former Soviet Union, 88.