(c)2001-2005 Mineral Data Publishing, version 1

Crystal Data: Triclinic. *Point Group:* $\overline{1}$. Typically as spherical or hemispherical aggregates of divergent crystals, acicular along [001], to 1 mm; individual crystals display prominent $\{010\}$, and narrow $\{2\overline{1}0\}$ and $\{102\}$.

Physical Properties: Cleavage: Perfect on $\{010\}$ and $\{2\overline{1}0\}$. Hardness = 3–4 D(meas.) = 2.80(2) D(calc.) = 2.817 Easily dehydrates to dresserite.

Optical Properties: Transparent to translucent. *Color:* Colorless. *Streak:* White. *Luster:* Vitreous.

Optical Class: Biaxial (–). Orientation: X (65°,88°); Y (–27°,46°); Z (158.25°,44.5°) [with c (0°,0°) and b^* (0°,90°) using (ϕ,ρ)]. $\alpha = 1.502(2)$ $\beta = 1.594(1)$ $\gamma = 1.595(1)$ 2V(meas.) = 17(1)°

Cell Data: Space Group: $P\overline{1}$. a = 9.7545(5) b = 10.4069(5) c = 5.6322(3) $\alpha = 95.695(5)^{\circ}$ $\beta = 92.273(5)^{\circ}$ $\gamma = 115.643(4)^{\circ}$ Z = 2

X-ray Powder Pattern: Francon quarry, Canada. 8.52 (10), 3.42 (7), 3.10 (6), 4.26 (5), 8.75 (4), 9.30 (3), 5.32 (3)

Chemistry:

	(1)	(2)
CO_2	21.8	20.31
Al_2O_3	23.7	23.53
BaO	35.0	35.38
${\rm H_2O}$	20.3	20.78
Total	100.8	100.00

(1) Francon quarry, Canada; by electron microprobe, corresponding to $Ba_{0.98}Al_{1.99}$ (CO_3)_{2.12}(OH)_{3.68} •2.97 H_2O . (2) $BaAl_2(CO_3)_2(OH)_4$ •3 H_2O .

Occurrence: Very rare, in vugs in metamorphosed limestone, near the contact zone of a dawsonite-rich silicocarbonatite sill.

Association: Dresserite, weloganite, quartz.

Distribution: From the Francon quarry, Montreal Island, Montreal, Quebec, Canada.

Name: For essential water and characteristic dehydration to *dresserite* under low humidity conditions.

Type Material: Geological Survey of Canada, Ottawa, 13936; Royal Ontario Museum, Toronto, Canada, M34547, M34600.

References: (1) Jambor, J.L., A.P. Sabina, and B.D. Sturman (1977) Hydrodresserite, a new Ba-Al carbonate from a silicocarbonatite sill, Montreal Island, Quebec. Can. Mineral., 15, 399–404. (2) (1979) Amer. Mineral., 64, 654 (abs. ref. 1). (3) Szymański, J.T. (1982) The crystal structure of hydrodresserite, $BaAl_2(CO_3)_2(OH)_4 \cdot 3H_2O$. Can. Mineral., 20, 253–262.