

## Rhodesite

## KH<sub>2</sub>Ca<sub>2</sub>Si<sub>8</sub>O<sub>19</sub>•5H<sub>2</sub>O

©2001 Mineral Data Publishing, version 1.2

**Crystal Data:** Orthorhombic. *Point Group:* 2/m 2/m 2/m. Matted silky fibers, some platy, to 2 mm. In flattened rosettes, irregular segregations, and crusts.

**Physical Properties:** Cleavage: Good, {100}. Hardness = ~4 D(meas.) = 2.27–2.36 D(calc.) = 2.26

**Optical Properties:** Translucent to transparent. Color: White. Luster: Silky. Optical Class: Biaxial (+). Orientation: X = b; Y = a; Z = c.  $\alpha = 1.501\text{--}1.504$   $\beta = 1.506\text{--}1.508$   $\gamma = 1.513\text{--}1.518$  2V(meas.) = n.d. 2V(calc.) = 68.1°

**Cell Data:** Space Group: Pmam. a = 23.42–23.79 b = 6.55–6.59 c = 7.01–7.06 Z = 2

**X-ray Powder Pattern:** Trinity Co., California, USA.  
6.548 (100), 4.386 (47), 5.901 (34), 6.302 (32), 5.032 (28), 2.864 (25), 2.762 (23)

Chemistry:	(1)	(2)	(3)
SiO <sub>2</sub>	61.83	66.27	63.50
Al <sub>2</sub> O <sub>3</sub>	0.29		
FeO	0.25		
MgO	0.08		
CaO	14.90	15.21	14.81
Na <sub>2</sub> O	4.93	0.33	
K <sub>2</sub> O	5.28	2.23	6.22
H <sub>2</sub> O	12.50	[15.96]	15.47
Total	100.06	[100.00]	100.00

(1) Kimberley, South Africa, average of two analyses. (2) Do.; by electron microprobe, H<sub>2</sub>O by difference. (3) KH<sub>2</sub>Ca<sub>2</sub>Si<sub>8</sub>O<sub>19</sub>•5H<sub>2</sub>O.

**Occurrence:** In a kimberlite pipe (Kimberley, South Africa); in a magadiite deposit localized in altered silicic lavas (Trinity Co., California, USA).

**Association:** Mountainite (Kimberley, South Africa); magadiite, montmorillonite (Trinity Co., California, USA).

**Distribution:** In South Africa, at the Bultfontein diamond mine, Kimberley, Cape Province. From near Redding, Trinity Co., California, USA. On the Zeilberg, near Maroldsweisach, Bavaria, Germany. From San Venanzo, near Terni, Lazio, Italy.

**Name:** For Cecil John Rhodes (1853–1902), British founder of the DeBeers Mining Company, also for Rhodes University, Grahamstown, South Africa, where the mineral was examined.

**Type Material:** The Natural History Museum, London, England, 1957,18; National Museum of Natural History, Washington, D.C., USA, 114793.

**References:** (1) Mountain, E.D. (1957) Rhodesite, a new mineral from the Bultfontein mine, Kimberley. *Mineral. Mag.*, 31, 607–610. (2) Gard, J.A., H.F.W. Taylor, and R.A. Chalmers (1957) An investigation of two minerals: rhodesite and mountainite. *Mineral. Mag.*, 31, 611–623. (3) (1958) Amer. Mineral., 43, 624 (abs. refs. 1 and 2). (4) Sheppard, R.A. and A.J. Gude, 3rd (1969) Rhodesite from Trinity County, California. *Amer. Mineral.*, 54, 251–255. (5) Hesse, K.-F. (1979) Die Kristallstruktur von Rhodésit, H<sub>2</sub>K<sub>2</sub>Ca<sub>4</sub>Si<sub>16</sub>O<sub>38</sub>•10H<sub>2</sub>O – ein Silikat mit verzweigten Doppelschichten. *Zeits. Krist.*, 149, 155–156 (in German). (6) Hesse, K.-F., F. Liebau, and S. Merlino (1992) Crystal structure of rhodesite, HK<sub>1-x</sub>Na<sub>x+2y</sub>Ca<sub>2-y</sub>{IB, 3, 2<sup>2</sup><sub>∞</sub>} [Si<sub>8</sub>O<sub>19</sub>] •(6-z)H<sub>2</sub>O, from three localities and its relation to other silicates with dreier double layers. *Zeits. Krist.*, 199, 25–48.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise without the prior written permission of Mineral Data Publishing.