

Teruggite

$\text{Ca}_4\text{MgAs}_2\text{B}_{12}\text{O}_{22}(\text{OH})_{12} \cdot 14\text{H}_2\text{O}$

©2001-2005 Mineral Data Publishing, version 1

Crystal Data: Monoclinic. *Point Group:* 2/m. Acicular [001] to tabular {100} crystals, prismatic {110} with rhomboidal cross-section, to 0.1 mm; aggregated into cauliflower-shaped nodules.

Physical Properties: Cleavage: On {001}, good; on {110}, fair. Tenacity: Brittle. Hardness = 2.5 D(meas.) = 2.149–2.20 D(calc.) = 2.192

Optical Properties: Transparent. Color: Colorless to white. Luster: Vitreous. Optical Class: Biaxial (+). Orientation: $Z = b$; $X \wedge c = -26^\circ$. Dispersion: $r > v$, weak. $\alpha = 1.526(1)$ $\beta = 1.528(1)$ $\gamma = 1.551(1)$ 2V(meas.) = 33°

Cell Data: Space Group: $P2_1/a$. $a = 15.675(13)$ $b = 19.920(14)$ $c = 6.255(4)$ $\beta = 99^\circ 20(5)'$ $Z = 2$

X-ray Powder Pattern: Loma Blanca deposit, Argentina.
12.13 (100b), 2.785 (30), 9.98 (22b), 3.577 (22b), 4.65 (21b), 8.37 (20b), 4.571 (17)

Chemistry:

	(1)	(2)
As_2O_5	17.99	18.06
B_2O_3	32.88	32.83
MgO	3.17	3.17
CaO	17.57	17.62
H_2O^+	25.57	
H_2O^-	2.82	
H_2O	28.32	
Total	[100.00]	100.00

(1) Loma Blanca deposit, Argentina; recalculated to 100% from an original total of 99.94% after deduction of SiO_2 0.29%; then corresponds to $\text{Ca}_{3.98}\text{Mg}_{1.00}\text{As}_{1.99}\text{B}_{12}\text{O}_{22}(\text{OH})_{12} \cdot 14\text{H}_2\text{O}$.

(2) $\text{Ca}_4\text{MgAs}_2\text{B}_{12}\text{O}_{22}(\text{OH})_{12} \cdot 14\text{H}_2\text{O}$.

Occurrence: In lacustrine borate deposits, typically associated with volcanic hot springs and diagensis of playa sediments.

Association: Inyoite, calcite, ulexite, aragonite, realgar, montmorillonite (Loma Blanca deposit, Argentina); colemanite, meyerhofferite, ulexite (Emet deposits, Turkey).

Distribution: From the Loma Blanca borate deposit, eight km southwest of Coranzulí, Jujuy Province, Argentina. At the Hisarcik borate mine, near Emet, Kütahya Province, Turkey.

Name: Honors Mario E. Teruggi, Professor of Sedimentology and Petrology, National University, Plata, Argentina.

Type Material: Harvard University, Cambridge, Massachusetts, 109056; National Museum of Natural History, Washington, D.C., USA, 145925.

References: (1) Aristarain, L.F. and C.S. Hurlbut, Jr. (1968) Teruggite, $4\text{CaO} \cdot \text{MgO} \cdot 6\text{B}_2\text{O}_3 \cdot \text{As}_2\text{O}_5 \cdot 18\text{H}_2\text{O}$, a new mineral from Jujuy, Argentina. Amer. Mineral., 53, 1815–1827.
(2) Dal Negro, A., I. Kumbasar, and L. Ungaretti (1973) The crystal structure of teruggite. Amer. Mineral., 58, 1034–1043.